



Values shown are average values determined from laboratory tests.

LAST-A-FOAM® EF-4003 FLEXIBLE POLYURETHANE FOAM			
Property	English	Metric	Test Method
Density (pcf) (kg/m <sup>3</sup> )	3.0	48	ASTM D-3574
Compression Load vs. Deflection (psi) (kPa)			ASTM D-3574
@ 75°F: Stress at 10%	2.6	18	
@ 75°F: Stress at 20%	2.7	19	
@ 75°F: Stress at 30%	2.8	19	
@ 75°F: Stress at 40%	3.0	21	
@ 75°F: Stress at 50%	3.4	23	
@ 75°F: Stress at 60%	4.2	29	
@ 75°F: Stress at 70%	5.9	41	
Tensile Strength (psi) (kPa)	19	134	ASTM D-3574
Ultimate Elongation (%) (%)	80	552	ASTM D-3574
Compression Set (%) (%)	-1.9%	-1.9%	ASTM D-3574
Resilience (%) (%)	33.0%	33.0%	ASTM D-3574

11/19/2015

**GENERAL PLASTICS MANUFACTURING COMPANY**  
4910 BURLINGTON WAY  
TACOMA, WA 98409  
phone (253) 473-5000 fax (253) 473-5104  
e-mail: [sales@generalplastics.com](mailto:sales@generalplastics.com)  
website: [www.generalplastics.com](http://www.generalplastics.com)

This data is subject to revision and changes due to development of and changes to the material. The data is derived from tests and historical usage. The data is averaged data and should be treated as such. Calculations should be verified by actual tests. The data is furnished without liability for the company and does not constitute a warranty or representation in respect to the material or its use. The company reserves the right to release new data sheets in replacement.