



LAST-A-FOAM® FP-8015 SEMI-RIGID POLYURETHANE FOAM			
Property	English	Metric	Test Method
Density (pcf) (kg/m³)	15.0	240	ASTM D-3574
Load Deflection (psi) (kPa)			
Parallel to Rise			
@ 75°F: Stress at 25%	69	476	ASTM-D-1621
@ 75°F: Stress at 50%	175	1207	ASTM-D-3574
@ 150°F: Stress at 25%	18	124	ASTM-D-1621
Tensile Strength (psi) (kPa)			ASTM D-3574
Parallel to Rise	133	917	
Tensile Modulus (psi) (kPa)			ASTM D-3574
Parallel to Rise	689	4751	
Shear Strength (psi) (kPa)			ASTM C-273 Compression Shear
Rise Parallel to Specimen Width	117	807	
Rise Parallel to Specimen Thick.	134	924	
Shear Modulus (psi) (kPa)			ASTM C-273 Compression Shear
Rise Parallel to Specimen Width	421	2903	
Rise Parallel to Specimen Thick.	447	3082	
Flexural Strength (psi) (kPa)			ASTM D-790 Procedure B
Rise Parallel to Beam Thick.	43	296	
Flexural Modulus (psi) (kPa)			
Rise Parallel to Beam Thick.	931	6419	
Dynamic Load Deflection:			General Plastics Test Plan G-TP9201-1
Impact Energy (in-lbs) (Kg-meters)	2820.3	389.9	
Rebound (Resilience) Energy (in-lbs) (Kg-meters)	279.5	3.2	
Acceleration, g-max (g)	129.3	129.3	
Glass Transition, T_g (°F) (°C)	109	43	TMA
Fire Safety	Pass	Pass	<15s extinguish time, <6 in burn length *via test method shown below

Values shown are average values determined from laboratory tests

06/16/2011

*FAR 25.853 (A) App. F (a)(1)(ii) tested vertically on 1/2" thick specimen using 12-second ignition with a Bunsen burner

GENERAL PLASTICS MANUFACTURING COMPANY
4910 BURLINGTON WAY
TACOMA, WA 98409
phone (253) 473-5000 fax (253) 473-5104
e-mail: sales@generalplastics.com
website: www.generalplastics.com

This data is subject to revision and changes due to development of and changes to the material. The data is derived from tests and historical usage. The data is averaged data and should be treated as such. Calculations should be verified by actual tests. The data is furnished without liability for the company and does not constitute a warranty or representation in respect to the material or its use. The company reserves the right to release new data sheets in replacement.