



FOAMCOMB			
Property	English	Metric	Test Method
Density (pcf) (kg/m ³)	*6.6	*106	*ASTM D-1622
Compression Test (psi) (kPa) Stress @ 33%	*2.3	*16	*GPS-9208
Fire Safety	**S/E	**S/E	**Self-extinguishing via test method shown below

*Maximum allowable values to meet the GPS-9208 specification.

4/30/2015

Density and compression testing are performed at room temperature. Burn temperature for vertical flammability testing is 1550°F, as required by FAR 25.853, App F

**Tested vertically on 0.4" thick specimen using 12- second ignition with a Bunsen burner

GENERAL PLASTICS MANUFACTURING COMPANY
4910 BURLINGTON WAY

TACOMA, WA 98409

phone (253) 473-5000 fax (253) 473-5104

e-mail: sales@generalplastics.com

website: www.generalplastics.com