



LAST-A-FOAM® TF-5070-13 FLEXIBLE POLYURETHANE FOAM			
Property	English	Metric	Test Method
Density (pcf) (kg/m <sup>3</sup> )	13.0	208	ASTM D-3574
Load Deflection (psi) (kPa)			ASTM D-3574
@ 75°F: Stress at 25%	11	72	
@ 75°F: Stress at 50%	17	118	
Percent Compression (%) (%)			ASTM D-3574
@ 75°F	4	4	
@ 158°F	4	4	
Resilience (%) (%)			ASTM D-3574
@ 75°F	49	49	
Fire Safety	Pass	Pass	<10s extinguish time, <4 in burn length, <1s drip extinguish time *via test method shown below

Values shown are average values determined from laboratory tests. Material properties are customizable. Please contact the Sales Department to set specifications.

10/17/2012

\*FAR 25.853 (A) App. F (a)(1)(ii) tested vertically on 1/2" thick specimen using 12-second ignition with a Bunsen burner

GENERAL PLASTICS MANUFACTURING COMPANY  
4910 BURLINGTON WAY  
TACOMA, WA 98409  
phone (253) 473-5000 fax (253) 473-5104  
e-mail: sales@generalplastics.com  
website: www.generalplastics.com

This data is subject to revision and changes due to development of and changes to the material. The data is derived from tests and historical usage. The data is averaged data and should be treated as such. Calculations should be verified by actual tests. The data is furnished without liability for the company and does not constitute a warranty or representation in respect to the material or its use. The company reserves the right to release new data sheets in replacement.