



LAST-A-FOAM® TF-6070-8.5 FLEXIBLE POLYURETHANE FOAM			
Property	English	Metric	Test Method
Density (pcf) (kg/m ³)	8.5	136	ASTM D3574
Compression Load vs. Deflection (psi) (kPa)			ASTM D3574
@ 75°F: Stress at 10%	9.7	67	
@ 75°F: Stress at 50%	16.7	115	

Values shown are average values determined from laboratory tests

08/17/2015

This data is subject to revision and changes due to development of and changes to the material. The data is derived from tests and historical usage. The data is averaged data and should be treated as such. Calculations should be verified by actual tests. The data is furnished without liability for the company and does not constitute a warranty or representation in respect to the material or its use. The company reserves the right to release new data sheets in replacement.

GENERAL PLASTICS MANUFACTURING COMPANY
 4910 BURLINGTON WAY
 TACOMA, WA 98409
 phone (253) 473-5000 fax (253) 473-5104
 e-mail: sales@generalplastics.com
 website: www.generalplastics.com