



LAST-A-FOAM® FR-4300 RIGID POLYURETHANE FOAM

PROPERTY	UNIT	FR-4305	FR-4310	FR-4315	TEST METHOD
Density	lbs/ft ³	5	10	15	ASTM D-1622
	kg/m ³	80	160	240	
Compressive Strength (75°F)	psi	100	300	560	ASTM D-1621
	kPa	690	2,050	3,850	
Tensile Strength	psi	150	400	650	ASTM D-1623 Type A Specimens
	kPa	1,050	2,750	4,500	
Flexural Strength	psi	70	340	820	ASTM D-790 Method 1-A
	kPa	480	2,350	5,650	

Values shown are parallel to the direction of rise and representative values

4/4/2018

GENERAL PLASTICS MANUFACTURING COMPANY

4910 BURLINGTON WAY

TACOMA, WA 98409

phone (253) 473-5000 fax (253) 473-5104

e-mail: sales@generalplastics.com

website: www.generalplastics.com

This data is subject to revision and changes due to development of and changes to the material. The data is derived from tests and historical usage. The data is averaged data and should be treated as such. Calculations should be verified by actual tests. The data is furnished without liability for the company and does not constitute a warranty or representation in respect to the material or its use. The company reserves the right to release new data sheets in replacement.