



LAST-A-FOAM® FR-4700 RIGID POLYURETHANE FOAM

PROPERTY	UNIT	FR-4718	FR-4730	FR-4740	TEST METHOD
Density	lbs/ft ³	18	30	40	ASTM D-1622
	kg/m ³	288	481	641	
Compressive Strength (75°F)	psi	1,200	3,000	5,200	ASTM D-1621
	kPa	8,250	20,700	35,900	
Coefficient of Thermal Expansion (CTE)	in/in-°F	26 x 10 ⁻⁶			From -50 to +200°F, GP Method
	m/m-K	47 x 10 ⁻⁶			
Max Use Temperature	°F	400			
	°C	204			

Values shown are parallel to the direction of rise and representative values

4/4/2018

GENERAL PLASTICS MANUFACTURING COMPANY

4910 BURLINGTON WAY

TACOMA, WA 98409

phone (253) 473-5000 fax (253) 473-5104

e-mail: sales@generalplastics.com

website: www.generalplastics.com

This data is subject to revision and changes due to development of and changes to the material. The data is derived from tests and historical usage. The data is averaged data and should be treated as such. Calculations should be verified by actual tests. The data is furnished without liability for the company and does not constitute a warranty or representation in respect to the material or its use. The company reserves the right to release new data sheets in replacement.