



LAST-A-FOAM® R-9300 RIGID POLYURETHANE FOAM (Metric Units)

Property	Test Method	R-9320	R-9325	R-9330	R-9335	R-9340	R-9340HP
Density (kg/m ³)	ASTM D-1622	320	400	481	561	641	641
Compressive Strength (kPa)							
Parallel to Rise, Strength @2% Deflection*							
24°C	ASTM-D-1621	2,400	3,450	6,900	10,350	12,400	14,500
Parallel to Rise, Strength @10% Deflection							
24°C	ASTM-D-1621	7,250	12,150	16,350	23,000	29,100	29,100
Compressive Modulus (kPa)							
Parallel to Rise @10% Deflection							
24°C	ASTM-D-1621	257,000	423,500	624,000	686,000	786,000	786,000
93°C		136,500	225,000	240,500	379,000	379,000	379,000
Perpendicular to Rise @10% Deflection							
24°C	ASTM-D-1621	194,500	325,500	436,000	627,500	800,000	800,000
93°C		109,500	172,500	229,000	293,000	358,500	358,500
Tensile Strength (kPa)							
Parallel to Rise	ASTM D-1623 Type A Specimens	5,150	7,600	9,650	13,100	15,900	15,900
Perpendicular to Rise		4,900	7,250	8,700	13,100	17,200	17,200
Shear Strength (kPa)							
Parallel to Rise	ASTM C-273 in Compression *Modified sample size = 0.64cm x 2.54cm x 7.62cm	4,300	6,550	8,800	10,700	11,900	11,900
Flexural Strength (kPa)							
Rise Parallel to Test Span	ASTM D-790 Method 1-A	7,050	10,700	13,400	18,600	23,450	23,450
Rise Parallel to Beam Thick.		6,850	10,700	13,450	19,300	24,150	24,150
Flexural Modulus (kPa)							
Rise Parallel to Test Span	ASTM D-790 Method 1-A	229,000	382,000	495,000	710,000	896,500	896,500
Rise Parallel to Beam Thick.		229,000	380,000	487,500	703,500	896,500	896,500
Thermal Conductivity: (W/m-K)	ASTM C-518 at 24°C mean temp.	5.6×10^{-2}	6.5×10^{-2}	7.4×10^{-2}	8.3×10^{-2}	9.2×10^{-2}	9.2×10^{-2}
R-Value [(K-m²/W)]		0.45	0.39	0.34	0.31	0.28	0.28
Coefficient of Thermal Expansion: (m/m-K)	From -46 to +93°C, GP Method	56×10^{-6}					
Poisson's Ratio:	Literature (Gibson & Ashby)	~ 0.3					
Glass Transition Temperature, Tg (°C)	ASTM E-1824	116					
Max Use Temperature (°C)		104					
Fire Safety	Self-extinguishing via FAR 25.853 (A) App. F (a)(1)(i) & (ii) tested vertically on 1.27cm thick specimen using 12- and 60- second ignition with a Bunsen burner						

10/14/2022

* Compressive Strength values are certified to exceed shown minimum values, all other values are nominal.

The data is derived from tests and historical usage. The data is averaged data and should be treated as such. These values do not constitute a sales specification, except as noted for the compressive strength values.

GENERAL PLASTICS MANUFACTURING COMPANY

4910 BURLINGTON WAY, TACOMA, WA 98409 | phone (253) 473-5000 | fax (253) 473-5104
e-mail: sales@generalplastics.com | website: www.generalplastics.com