



LAST-A-FOAM® R-9300 RIGID POLYURETHANE FOAM

PROPERTY	UNIT	R-9320	R-9325	R-9330	R-9335	R-9340	R-9340 HP	TEST METHOD
Density	lbs/ft ³	20	25	30	35	40	40	ASTM D-1622
	kg/m ³	320	400	481	561	641	641	
Compressive Strength (75°F Strength at 2% Deflection)	psi	350	500	1,000	1,500	1,800	2,100	ASTM D-1621
	kPa	2,400	3,450	6,900	10,350	12,400	14,500	Certified minimum value
Tensile Strength	psi	700	1,000	1,200	1,500	1,800	1,900	ASTM D-1623 Type A Specimens
	kPa	4,850	6,900	8,250	10,350	12,400	13,100	
Shear Strength	psi	590	980	1,275	1,500	1,725	1,800	ASTM C273 in Compression
	kPa	4,050	6,750	8,800	10,300	11,900	12,400	*Modified sample size = 0.25"x1.0"x3.0"

Values shown are parallel to the direction of rise and representative values

4/4/2018

GENERAL PLASTICS MANUFACTURING COMPANY

4910 BURLINGTON WAY

TACOMA, WA 98409

phone (253) 473-5000 fax (253) 473-5104

e-mail: sales@generalplastics.com

website: www.generalplastics.com

This data is subject to revision and changes due to development of and changes to the material. The data is derived from tests and historical usage. The data is averaged data and should be treated as such. Calculations should be verified by actual tests. The data is furnished without liability for the company and does not constitute a warranty or representation in respect to the material or its use. The company reserves the right to release new data sheets in replacement.